

Product information | TECHNICAL DATA SHEET

Pocket. Solid Colors. Low pressure, matt finishes.

150ml, 4 Oz, 112 g

GENERAL DESCRIPTION

Matt finish, very fast-drying alkyd enamel with excellent outdoor color durability.

FEATURES

- Very fast drying
- Good elasticity.
- Easy to apply and repaint.
- Hardens well.
- Does not contain lead nor other heavy metals.
- Good covering capability.
- Low pressure.
- Excellent resistance to the sun and rain.
- Long-lasting color.
- Very good resistance to UV light (see chart).
- Strong resistance to scratching once the film is polymerized.
- Its small size (150 ml) makes it a very practical tool.

INSTRUCTIONS FOR USE

- Shake the aerosol well before using, approximately for one minute after hearing the sound of the mixer.
- Apply to clean, dry surfaces. On rusty metallic surfaces remove rust with a wire brush and prepare an anti-rust primer if considered necessary. Apply an anchor layer on plastics and polyesters.
- For best results apply in thin layers. Three thin layers are always better than one thick one, and may be repainted within fifteen minutes with the same paint.
- Turn the aerosol upside down to clean out the valve after use. If te nozzle becomes blocked replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas.
- Request safety datasheets.

PHYSICAL PROPERTIES

Type of liant:	Modified alkyd
Color:	See chart
Shine 60° (ASTM D-523 ISO 2813):	15-25% Matt
Dry to the touch (ASTM D-1640 ISO 1517):	10'
Completely dry (ASTM D-1640 ISO 1517):	24 h
Thickness of dry layer (ASTM D-823 ISO 2808):	15 micras/layer
Adherence (ASTM D-3359 ISO 2409):	0 B
Theorical yield (continuous painting):	0,75 m ² for 150 ml
Thinner:	Mixture
Product life:	(Well Stored) 10 years
Condition for application:	Minimum room temperature 8°C
	Surface temperature 5°C a 50°C
	Max humidity . 85% R.H.P
Heat resistance of paint:	100°C
Second coat:	After 15 'before 2 h or after 48

^{*} All of the adherence tests have been carried out on steel plates.

CAUTION













APPLICATIONS

Due to the characteristics of this product we recommend its use for touch-ups and painting of all types of materials for either indoor or outdoor jobs. Suitable for home projects, crafts, fine arts, and generally where the properties of a high quality spray paint are required.

- Graffiti
- Gardening Fine Arts
- Construction
- DIY Sign painting Aluminum framing

APPEARANCE



.ID

Protects the valve. and the nozzle.

LABEL CAP SYSTEM







PACKAGING

Low pressure.

Nominal capacity: 150 ml.

Heat resistanve of packaging: <50°C Propellant: GLP - HC C₃-C₄

COLORS









Product information | TECHNICAL DATA SHEET

Pocket. Metallic Colors. Silver.

150ml, 4 Oz, 112 g

GENERAL DESCRIPTION

The Pocket's metallic silver paint is formulated with fast-drying solvent-based acrylic resins and metallic inorganic pigments.

FEATURES

- Low pressure.
- Very fast drying.
- Excellent adherence.
- Does not contain lead nor other heavy metals.
- Excellent metallic finish.
- Easy to apply and repaint with the same paint.
- May not be repainted or varnished with other paints.
- Non-resistant to abrasion.
- Low resistance to weathering.
- Does not contain anti-corrosive properties

INSTRUCTIONS FOR USE

- Shake the aerosol well before using, approximately for one minute after hearing the sound of the mixer.
- Apply to clean, dry surfaces. On rusty metallic surfaces remove rust with a wire brush and prepare an anti-rust primer if considered necessary. Apply a primer coat on plastics and polyesters.
- For best results apply in thin coats. Three thin coats are always better than one thick one, and may be repainted within fifteen minutes with the same paint.
- Turn the aerosol upside down to clean out the valve after use. If the nozzle becomes blocked replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas.
- Due to the nature of their pigments, these paints cannot be varnished or repainted with other solvent-based paints, except with Pocket paint.
- Request safety datasheets.

PHYSICAL PROPERTIES

Basse pression:	Polyvalent female valve
Propulseur:	Butane / Propane / Mix
Type of liant:	Ketonic
Color:	Silver
Appearance:	Shine
Dry to the touch (ASTM D-1640 ISO 1517):	10'
Completely dry (ASTM D-1640 ISO 1517):	2 h
Thickness of dry layer (ASTM D-823 ISO 2808):	15 micras/layer
Adherence(ASTM D-3359 ISO 2409):	0 B
Theorical yield (continuous painting):	1 m² for150 ml
Thinner:	Mixture
Product life:	(Well Stored) 10 years
Condition for application:	Minimum room temperature 8°C
	Surface temperature 5°C a 50°C
	Max humidity . 85% R.H.P
Heat resistance of paint:	100°C

^{*} All of the adherence tests have been carried out on iron plates

CAUTION













APPLICATIONS

Provides the painted surfaces with a silver metallic appearance with great decorative power, very suitable for plastic and artistic arts for interior use, since its resistance to the weather is very low.

- Creative jobs - DIY - Fine Arts - Graffiti - Crafts/hobby - Scenography
- **APPEARANCE**



Protects the valve and the nozzle.

LABEL **CAP SYSTEM**





COLOR



PACKAGING

Low pressure. Nominal capacity 150 ml. Heat resistanve of packaging: <50°C Propellant GLP - HC C3-C4



